

BTCAL - R (Macro) >> Bonded

Brown Fused Aluminum Oxide

BTCAL is a brown fused aluminum oxide obtained by a reduction fusion of high quality bauxites in electric arc furnaces. In order to improve its quality this material is calcined and present low dust content. It's recommended for high performance bonded abrasives. Produced according to ANSI or FEPA-F.

General Characteristics

True Specific Gravity	Friability (ANSI-B74.8R2007)
3.96 g/cm ³	46%

Bulk Density (g/cm³)

Grit Size	(LD) sharp	(R) cubic	(HD) super cubic
10	1.79	1.90	2.01
12	1.80	1.91	2.02
14	1.80	1.91	2.02
16	1.79	1.80	2.01
20	1.79	1.80	2.01
22	1.79	1.80	2.01
24	1.78	1.89	2.00
30	1.77	1.88	1.99
36	1.77	1.88	1.99
40	1.75	1.86	1.97
46	1.74	1.85	1.96
54	1.70	1.81	1.92
60	1.68	1.79	1.90
70	1.65	1.76	1.87
80	1.63	1.74	1.85
90	1.60	1.71	1.83
100	1.58	1.69	1.80
120	1.55	1.66	1.77
150	1.54	1.65	1.76
180	1.51	1.62	1.73
220	1.49	1.60	1.71

Chemical Analysis by XRF (%)

Al ₂ O ₃	TiO ₂	SiO ₂	Fe ₂ O ₃	MgO
95.61	2.55	0.90	0.23	0.32

FEPA 44 - 1:2006